

Cleanroom Glove Riverstone LE-Tacky

Article data

Specifications

Material:	100% Nitrile
Size:	6/XS - 11/XXL
Colour:	White
Thickness:	0.10mm ±0.02mm (Palm)
Length:	approx. 300 mm
ISO Class:	ISO 4 GMP C/D

Particle Count (0.5 - 20 micron)	< 400 count/cm ²
--	-----------------------------

Packaging:	<ul style="list-style-type: none"> • 100 pcs. per bag • 10 bags per carton
-------------------	--

Areas of application:	<ul style="list-style-type: none"> • Semiconductor industry • Pharmaceutical industry • Aviation • Electronics • Healthcare
------------------------------	--



Characteristics :

- Low levels of extractable substances
- Powder-free
- Latex-free
- Ambidextrous
- Textured fingertips for improved grip
- Very low particle emission
- Highly extensible, flexible and comfortable



TÜV Rheinland LGA Products GmbH
Tillystraße 2
D-90431 Nürnberg



Protective gloves against dangerous chemicals Liquid-tight gloves
Tested for NaOH 40% = Level 6
additional tested
Tested to IPA 100% = Level 1

PPE CATEGORY III

according to PPE Regulation VO (EU) 2016/425, §11A

Cleanroom Glove Riverstone LE-Tacky

Material:

- 100% pure Nitrile
- Without plasticizers, contain no phthalates esters, silicone oil and Amide
- No Sulphur , Accelerator & Zinc added during compounding process.

Process:

- Laundered with 0.1 micron filtered with high resistivity D.I water and packed in certified Class 10 (ISO 4) cleanroom environment.

Item number Size	330514 6/XS	330515 7/S	330516 8/M	330517 9/L	330518 10/XL	330519 11/XXL
Overall Length (± 10 mm)	300 mm	300 mm	300 mm	300 mm	300 mm	300 mm
Palm Width (± 5 mm)	78 mm	85 mm	95 mm	105 mm	115 mm	120 mm

ESD Specification @ RH 45-55%, Temp : 20-26C (Ref : ANSI/ESD-STM11.11 & ANSI/ESD SP15.1)

Surface Resistivity (Ohm/sq)	Decay Time (Second)	Tribo Charge (Volt)
≤10 ¹⁰	≤0.5	≤20

Physical Specification (Method Ref : ASTM D6319)

Tensile Strength (MPa)	Elongation at break (%)
Min 14.0	Min 500

Particle count Count/cm ² (0.5 - 20 mi- cron. cum)	Ion content						
	Maximum anions (µg/cm ²)						
< 400	F ⁻	Cl ⁻	NO ₂ ⁻	Br ⁻	NO ₃ ⁻	PO ₄ ³⁻	SO ₄ ²⁻
	< 0.005	< 0.1	< 0.005	< 0.02	< 0.1	< 0.005	< 0.02